

DISPOSABLE WINDOW


A not uncommon problem in some industrial environments, such as foundries, is maintaining optical cleanliness during washdown, or protecting the lens from debris when air purge is impractical or insufficient. In addition, sometimes a barrier is necessary between the process to be monitored and the IRt/c.

Windows made of common materials such as glass, etc. will significantly attenuate infrared radiation from targets below about 1000°F (540°C) and are not generally suitable for low temperature service. *However, windows made of polyethylene will transmit very efficiently at all temperatures if they are thin enough. "Thin" means generally less than about 0.005 in. (0.1 mm).*

An excellent material is a commonly available plastic wrap brand called *Glad*

Cling Wrap®, which can easily be wrapped around the IRt/c for cleanliness, or formed into a window. If the polyethylene is dirty or damaged, it can easily be replaced. With maximum temperature rating at about 212°F (100°C), this material can be used in many processes.

The transmission coefficient of such thin polyethylene is in the neighborhood of 90%, and therefore only a small recalibration of the readout device may be required. Other brands of plastic wrap are not recommended, unless you can confirm that they are made from polyethylene.



Exergen Global offices:

USA
400 Pleasant Street
Watertown, MA 02472
Tel: +1 617 923 9900 press 4 for industrial
Fax: +1 617 923 9911

The Netherlands
Pastoor Clercxstraat 26
5465 RH Veghel
Tel: +31 (0)413 376 599
Fax: +31 (0)413 379 310

industrial@exergen.com
www.exergen.com